


PHOTOVOLTAIC ONGRID OPTIMIZED MODULE

MODEL: ATI-2000(230W)



CERTIFICATION:

· ISO 9001







ATI 's module uses state of the art multicrystalline technology with a Silicon Nitride (SiN) coating that enhances cell efficiency. Encapsulation beneath high transmission tempered glass is accomplished using an advanced, UV resistant thermal setting plastic. The encapsulant, ethylene vinyl acetate, cushions the solar cells within the laminate and protect the cells from etching. The rear surface of the module is completely sealed from moisture and


ATI high efficiency module size is easy to handle and specifically

designed for large and small scale grid interactive applications.

ATI's module incorporates a reinforced anodised aluminium frame, designed to meet ATI's High Quality Standards for corrosion resistance.

mechanical damage by a continuous high strength polymer sheet.

STC Power Rating	230.0W @ STC	
CSI- PTC Power Rating	197.9W @ PTC	
Maximum Power Voltage (Vpm)	29.49V	
Maximum Power Current (Ipm)	7.80A	
Open Circuit Voltage (Voc)	37.20V	
Short Circuit Current (Isc)	8.39 A	
Cell Type / # Cells	Poly / 60 Series	
Nominal Voltage	20Vdc	
Maximum System Voltage	DC 600V	
Series Fuse Rating	15A	
Performance Tolerance	+- 3%	



Limited warranty : 25 years


3930-B Valley Blvd. Walnut, CA 91789 Tel:(909)468-1800 Fax:(909)468-9880 Tel:(909)468-1800 Fax:(909)468-9880




PHOTOVOLTAIC ONGRID OPTIMIZED MODULE


MODEL: ATI-2000(230W)

ABSOLUTE MAXIMUM RATINGS		
Parameters	Rating	Unit
Operating temperature	-40 to +90	$^{\circ}$
Storage temperature	-40 to +90	$^{\circ}$
Dielectric voltage withstood	2200 max	V-DC



36 Modules / Pallet	
1,922 LBS / Pallet	
130"H x 75"W x 55"L	





Temperature coefficient of Isc: 0.08%/°C

Power temperature coefficient: -0.38%/°C

Temperature coefficient of Voc: -0.32%/°C

NOCT:46±1°C

Limited warranty : 25 years

Walnut, CA 91789 Tel:(909)468-1800 Fax:(909)468-9880